


CIE 1931 Chromaticities of Solid State Lighting Phosphors



BOSE	$(\text{Ba,Sr})_2\text{SiO}_4:\text{Eu}$
BSNE	$\text{Ba}_2\text{Si}_5\text{N}_8:\text{Eu}$
BSON	$\text{BaSi}_2\text{N}_2\text{O}_2:\text{Eu}$
CSON	$\text{CaSi}_2\text{N}_2\text{O}_2:\text{Eu}$
ECAS	$\text{CaAlSiN}_3:\text{Eu}$
GdAG	$\text{Gd}_3\text{Al}_5\text{O}_{12}:\text{Ce}$
KSF	$\text{K}_2\text{SiF}_6:\text{Mn}$
LISE	$\text{SrLi}_2\text{SiO}_4:\text{Eu}$
LSAG	$\text{Lu}_3\text{Sc}_2\text{Al}_3\text{O}_{12}:\text{Ce}$
LuAG	$\text{Lu}_3\text{Al}_5\text{O}_{12}:\text{Ce}$
MGM	$\text{Mg}_4\text{GeO}_{5.5}\text{F}:\text{Mn}$
OSE	$(\text{Sr,Ca})_2\text{SiO}_4:\text{Eu}$
SAE	$\text{Sr}_4\text{Al}_{14}\text{O}_{25}:\text{Eu}$
SSON	$\text{SrSi}_2\text{N}_2\text{O}_2:\text{Eu}$
SSNE	$\text{Sr}_2\text{Si}_5\text{N}_8:\text{Eu}$
TAG	$\text{Tb}_3\text{Al}_5\text{O}_{12}:\text{Ce}$
YAG	$\text{Y}_3\text{Al}_5\text{O}_{12}:\text{Ce}$